



Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 10001

AEROSPACE RECOMMENDED PRACTICE

ARP 953A

Issued 11-15-66
Revised 5-31-68

STRESS DOME IN FASTENERS

1. PURPOSE - The purpose of this document is to establish limits or parameters for designing bolt heads with proper control of flowlines to assure sufficient strength to resist stresses induced by static or dynamic loads without being affected by lightening and lockwire holes.
2. DESIGN CONSIDERATIONS
 - 2.1 Heads may be cold or hot upset at a temperature compatible with the material being worked prior to heat treatment.
 - 2.2 The grain flow between the head and shank shall flow smoothly around the fillet radius and be unbroken, as shown by Figs. 1 and 2.
 - 2.3 To assure retention of good grain flow, the amount of metal to be removed per surface, for removal of contamination or decarburization, shall be within the limits specified in the applicable AMS specification.
 - 2.4 Height of bolt head should be such as to assure enough metal for flowlines to contour smoothly and evenly so that the stress dome is not flattened or compressed.
 - 2.5 If center lightening holes are used, the bottom of the hole shall not encroach into the stress dome area. These holes may either be forged or drilled with flat or angular bottoms, depending upon the part manufacturer's process, as specified on the part drawing. Lockwire holes also shall not encroach in the stress dome area.
 - 2.6 Figs. 1, 2, and 3 depict the flowline configurations which are acceptable and unacceptable. Sections are through major diameter of shank.
 - a. Fig. 1 shows a smooth unbroken grain flow pattern. This is the preferable condition.
 - b. Fig. 2 shows the maximum acceptable cutting of grain flow and minimum stress dome height.
 - c. Fig. 3 shows excessive cutting of grain flow in the shank, fillet, and bearing surface. This is not acceptable.
3. INSPECTION
 - 3.1 To determine whether or not the parts are in accordance with flowline requirements, the following method may be used.
 - 3.1.1 Section the specimen parts and macroetch or microetch to determine the flowline pattern. A suitable etching solution may be used. A 10X magnification may be used to show conformance, or non-conformance, with the flowline patterns in the Figures.

PREPARED BY COMMITTEE E-21,
DESIGN AND GENERAL STANDARDS FOR AEROSPACE PROPULSION SYSTEMS

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."